



## Filamentos Sierra Sur

Address : Avda Tomas Alba Esison 4  
post code : 18320 Santa Fe GRANADA (SPAIN)  
Contact Number : +34687910122 / +34626542488  
Email Address : [Export@filamentossierrasur.com](mailto:Export@filamentossierrasur.com)  
Website URL : <https://www.filamentos.info/>

### TECHINAL DATA SHEET LDPE



MATERIAL	LDPE RECYCLED	
FORM	PELLETS	
COLOUR	HONEY	
INPUT	GREENHOUSE AG-FILM	
TEST	VALUE	<u>UNIT</u>
DENSITY	0.944 ± 0.003	lcm3
MIFI (190°C;2.160)	0.882 ± 0.02	110min
ASH CONTENT	1.01	
TENSILE STRENGHT	11,88	(Mpa)
ELONGATION AT BREAK	469.08	

Ldpe particles other tan granules = absent

Extruder filter = 110 mesh

Storage and handling: the material is supplied in 1000-1200 kg big bags. Other presentations are possible upon request. It is advisable to store in a ventilated and dry place, protected from light and weather impacts. .

All information in this datasheet is provided in good faith and is based on our current knowledge and experience. The data above represent typical values and should not be construed as guaranteed specifications. It is the buyer's responsibility to determine the suitability of the product under the actual conditions of intended application.